

# POLISHING OPALINE™ SM2

## IDENTIFICATION AND GENERAL CHARACTERISTICS :

**Formula**      CeO<sub>2</sub>

Fine white powder

**ORIGIN**      La Rochelle France

## TECHNICAL CHARACTERISTICS

|                                |                   |           |
|--------------------------------|-------------------|-----------|
| LOI                            | %                 | 0.2       |
| Fe <sub>2</sub> O <sub>3</sub> | ppm               | 100       |
| Tap density                    | g/cm <sup>3</sup> | 1.4 - 1.9 |
| 15 µm oversize                 | ppm               | <= 50     |
| D.50 Sed                       | µm                | 0.4 - 0.6 |
| SA                             | m <sup>2</sup> /g | 3 - 5     |
| Retained on<br>1µm screen      | %                 | <= 8      |

  

|                  |             |      |
|------------------|-------------|------|
| CeO <sub>2</sub> | %/total REO | >=99 |
|------------------|-------------|------|

**PACKAGING**      20 kg plastic pails(540kg per pallet)

**REF 28388**

## SAFETY - STORAGE - HANDLING - LABELLING - TRANSPORTATION AND REGISTRATIONS

Please consult our Material Safety Data Sheet

The information contained in this document is given in good faith based on our current knowledge.

It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products.

The analytical methods used are described in our current quality control standards.

We reserve the right to modify the content of this technical data sheet without prior notification.

( \* *TM* Trade Mark of Rhodia Electronics & Catalysis )